



VOC XP

Sales Specifications

VOC XP

Sales Specifications	Min	Max	Test Method
MOISTURE (AS PACKAGED), wt%	-	5	ASTM D2867
HARDNESS NUMBER	T&R	-	ASTM D3802
ASH, wt%	-	15	ASTM D2866
IODINE NUMBER, mg/g	750	-	ASTM D4607
< 6 US MESH [3.35 mm] (PELLET), wt%	-	15	ASTM D2862

Chemviron Carbon's activated carbon products are continuously being improved and changes may have taken place since this publication went to press.

(12584 - 12/10/15)